SYNERGIST FOR FLAME RETARDANT NYLONS

Publication number: EP1068263

Publication date:

2001-01-17

Inventor:

MARTENS MARVIN MICHAEL (US); KOSHIDA REIKO

(JP); TOBIN WENDY (CA); WILLIS JOYCELYN M (CA)

Applicant:

DU PONT (US)

Classification:

- international:

C08K3/00; C08K3/38; C08K5/03; C08K3/00; C08K5/00; (IPC1-7): C08K3/00; C08K13/02; C08L77/00; C08K3/00;

C08K3/00; C08K3/00; C08K3/38; C08K13/02; C08K3/38;

C08K5/00

- european:

C08K3/00P; C08K3/38; C08K5/03

Application number: EP19990912654 19990318

Priority number(s): WO1999US05902 19990318; US19980078392P

19980318

Also published as:

WO9947597 (A1) EP1068263 (A0) CA2322286 (A1)

Report a data error here

Abstract not available for EP1068263

Abstract of corresponding document: WO9947597

Antimony-free polyamide molding compositions are disclosed having improved flame resistance. These compositions comprise, in with percent, 20-77 % polyamide having a melting point of 215-340 DEG C; 10-60 % inorganic filler; 10-35 % of a flame retardant having 50-70 % bormine; 3-10 % zinc borate; and, 0-2 % of a heat stabilizer.

Data supplied from the esp@cenet database - Worldwide